

This material is a vacuum casting polyurethane resin which similar to ABS and has good cost-performance. It suitable for moulding of large-sized prototype parts.

MECHANICAL PROPERTIES	
Hardness	84 Shore D
Tensile strength	60 MPa
Bending strength	80 MPa
Flexural modulus	2000 MPa
Elongation	15%
Impact strength	14 kJ/m²
Heat deflection temperature	100 °C
Shrinkage	0.3%

5 DD@7 5 HCB

Ü^+ã^|æ|Âæã*•
V^|çãã}Â}&[•~|^•
Ó{]^!Â^&ã}•